



Container, Trucks Waterproof & Anti-Corrosion (TH8031)

Polyurea elastomer is a compound formed by the reaction of isocyanate component (component A) and amino compound component (component R).

Spray polyurea elastomer (SPUA) technology is a new solvent-free and pollution-free green construction technology developed to meet the needs of environmental protection after (pollution-free) coating technologies such as high solid coating, water-based coating, radiation curing coating and powder coating in recent 20 years.

Office: +86(574)8388 2233

Dongxi, Xinqiao, Xiangshan
Ningbo 315725, P.R.China

info@yuxi-anode.com

www.yuxi-anode.com

- ▶ Train carriage
- ▶ Container
- ▶ Pickup trucks
- ▶ Battery box



FEATURES

- ▶ Good adhesion to various substrates
- ▶ Excellent corrosion resistance and chemical resistance
- ▶ Not sensitive to humidity, high and low temperature environment, good thermal stability
- ▶ Good environmental protection, solvent-free, safe construction and environment-friendly
- ▶ The coating is dense and continuous without seams, resistant to abrasion, impact and cathodic disbondment
- ▶ Excellent physical properties, high tensile strength, high tear strength, high electrical strength and high hardness
- ▶ Mechanized construction, fast curing to form a film, can be sprayed and formed on any special-shaped surface without sagging

ATTENTION

- ▶ During construction, the substrate temperature must be 3°C higher than the dew point temperature
- ▶ Before using the product, component B should be fully stirred
- ▶ The system is 100% solid content, and diluent is strictly prohibited
- ▶ Good ventilation must be maintained during construction in confined space
- ▶ When using this product, you must wear work clothes, gloves, goggles, gas masks and other protective equipment

SPECIFICATIONS

Items	Parameters
	TH-8031
Solid Content (%)	99
Gel Time (s)	15
Surface Dry Time (s)	2
Hardness (Shore D)	56
Impact Resistance (kg/m)	2.0
Cathodic Disbondment Resistance [1.5V, (65±5)°C, 48h]	No blistering, peeling distance ≤15mm
Tensile Strength (MPa)	22
Elongation at Break (%)	150
Tear Strength (N/mm)	65
Adhesion (MPa)	11
Electric Strength (MV/m)	30
Salt Spray Resistance (2000h)	No embroidering, no blistering, no shedding
Water Resistance (30d)	No embroidering, no blistering, no shedding
Oil Resistance (0# diesel, crude oil, 30d)	No embroidering, no blistering, no shedding
Liquid Medium Resistance (10%H ₂ SO ₄ , 10%HCl, 10%NaOH, 10%NaCl, 30d)	No embroidering, no blistering, no shedding

Product Ratio

Material A : material B = 1:1

Material A: 220kg/barrel; material B: 210kg/barrel

Product storage

Storage temperature: 5-40 °C

Under normal storage and transportation conditions, the storage period shall not be less than 6 months from the date of production

Store in a cool and ventilated environment, avoid direct sunlight, do not approach the fire source and prevent collision