



PRODUCT DATA SHEET













HEAT TREATER ALUMINUM ANODE ROD

Casted from high-voltage and high-potential alloy, our aluminum anode is designed to meet the standard GALVALUM III, containing nominal amounts of indium, zinc, and silicon. It has a proven track record for delivering superior cathodic protection for any type of structure requiring a compact solution in highly corrosive saltwater/brines with elevated temperatures. It is typically applied in heater treaters, heat exchangers, salt water storage tanks, oilfield tanks, skimmers, oil-separation vessels, pressure vessels and other production vessels.

This anode can be assembled with high compression molded fiberglass anode mount caps (blue or red). The red one can be installed in standard 4" SCH 40 fittings with grooved couplings. The blue one can be used for mounting in standard 4" SCH 80 fittings with grooved couplings.



CHEMICAL COMPOSITION

Element	Content (%)	
Zinc	(Zn)	2.000 ~ 6.000
Indium	(In)	0.010 ~ 0.020
Silicon	(Si)	0.080 ~ 0.200
Iron	(Fe)	0.130 max.
Copper	(Cu)	0.006 max.
Cadmium	(Cd)	_
Other Impurities		0.100 max.
Aluminum	(AI)	Remainder



ELECTROCHEMICAL PROPERTIES

Technical Measurement	Performance		
Open Circuit Voltage (min)	-1.10 Volts		
Closed Circuit Voltage (min)	-1.05 Volts		
Current Capacity	2500 A.h/kg (1135 A.h/lbs)		
Current Efficiency (min)	90%		
Consumption Rate	3.4 kg/A.y (7.6 lbs/A.y)		

* The open/closed circuit voltage is with respect to a Ag/AgCl reference electrode.








HEAT TREATER ALUMINUM ANODE ROD


SPECIFICATIONS



Item No.	Diameter	Length	Core Size	Net Weight	Gross Weight
YX-AL-R30	76mm (3")	762mm (30")	³ / ₄ " - 10UNC	8.4kg (18.5 lbs)	10kg (22 lbs)
YX-AL-R30	76mm (3")	1524mm (60")	³ / ₄ " - 10UNC	16.8kg (37.0 lbs)	20kg (44 lbs)

Note: All dimensions and weights shown above are nominal. The information provided is subject to change without notice.







www.yuxi-anode.com

6/F, Tianlu Building, 767 Liangzhu Road,

Ningbo 315000, P.R. China

E-mail: info@yuxi-anode.com

Tel: +86 (574) 8388 2233 **Fax:** +86 (574) 8388 2238